



“like water off a duck`s back”

PCT HYDROPHOBIC BRICK AND SLASTO VARNISH

PRODUCT CODE D-001

Revision 2.1

05/03/2014

APPLICATION PROCEDURE

SURFACE PREPARATION.

- Thoroughly remove all dust, dirt or any foreign debris.
- Remove all loose or flaking paint or varnish.
- Leave to dry.

APPLICATION

- Thin the first coat by adding 1 litre of clean potable water, stir well and apply to the surface by means of brush or roller application.
- Leave for 4 hours to allow for curing.
- Apply a second coat unthinned.
- Leave for 4 hours to allow for full cure.

CLEANING OF EQUIPMENT AND UTENSILS.

Use clean potable water.

MAINTENANCE

In the event of mechanical damage to the film, feather the edges with 80 grit sandpaper and apply 1 alternatively 2 coats and leave to dry.

The information contained in this document is meant as a guide for the specifier or user. It is gained from laboratory tests conducted in controlled environment and experience. No guarantee of performance is implied since application procedure, conditions of use, substrate condition and substrate cleanliness is beyond our control.

MANUFACTURED BY:

PCT WATER REPELLENT TECHNOLOGY CC

DISTRIBUTED BY:

MARVEL COATINGS
5 LOUIS TRICHARD STR
EXTENSION 10
WITBANK
1035

Tel: 013 656 4994

Fax: 086 623 7944

Cell: 072 404 1625

e-mail: info@marvelcoatings.co.za

web: www.marvelcoatings.co.za